

## Biond Bio-Print Film P GB BF 90

Biond product that offers a biobased film, free from plasticizers, with a 90-micron thickness, a permanent greyback adhesive and a bubble-free liner of 135 g/m<sup>2</sup>, that ensures high stability during printing. Recommended for a wide range of short- and medium-term promotional applications.

### Face Film

Bio-based Film with > 80% bio-components

| Finish                       | White Glossy                                                                       | White Matte |           |                          |
|------------------------------|------------------------------------------------------------------------------------|-------------|-----------|--------------------------|
|                              | Value                                                                              |             | Tolerance | Standard                 |
| Thickness (µm)               | 90                                                                                 | 90          | ± 5%      | Digidelta Test Method    |
| Grammage (g/m <sup>2</sup> ) | 100                                                                                | 100         | ± 10%     | Digidelta Test Method    |
| Gloss (60°C) (%)             | ≥ 75                                                                               | ≤ 15        | ± 10 %    | Digidelta Test Method    |
| Bio-based content (%)        | 85                                                                                 |             |           | EN 16640:2017/ASTM D6866 |
| Tensile strenght (MPa)       | > 30                                                                               |             |           | ASTM D412                |
| Elongation (%)               | > 250                                                                              |             |           | ASTM D412                |
| Modulus (MPa)                | 24                                                                                 |             |           | ASTM D412                |
| Flammability (FR)            | A2-s1, d0                                                                          |             |           | ISO 13501-1/ISO 11925-2  |
| Expected durability          | Up to 3 years outdoor and 5 years with Biond overlamination/ Up to 10 years indoor |             |           |                          |

### Adhesive

Clear acrylic based, permanent greyback bubble free adhesive

|                                     | Value       | Standard    |
|-------------------------------------|-------------|-------------|
| Peel Adhesion 20 min steel (N/25mm) | > 9         | FINAT FTM1  |
| Peel Adhesion 24 h steel (N/25mm)   | > 17        | FINAT FTM1  |
| Shrinkage (mm)                      | Max. 0,1    | FINAT FTM14 |
| Application Temperature (°C)        | > 10 °C     |             |
| Service Temperature (°C)            | -10 a 90 °C |             |

### Liner

Coated double PE embossed paper

|                              | Value | Tolerance | Standard              |
|------------------------------|-------|-----------|-----------------------|
| Thickness (µm)               | 148   | ± 5 µm    | Digidelta Test Method |
| Grammage (g/m <sup>2</sup> ) | 135   | ± 5 %     | Digidelta Test Method |

## Biond Bio-Print Film P GB BF 90

### Durability

• Indoor: up to 10 years (unprocessed and without sun exposure). • Outdoor: up to 3 years/5 years with Biond overlamination (unprocessed and applied under vertical exposure normal Central European climate). • Storage: 24 months, applicable only to unprocessed material under the following STORAGE CONDITIONS: • Store at a temperature of 20°C ± 5°C and 50 ± 5% relative humidity, avoiding major climatic variations. • The storage area must be dry and clean. • Keep the material in its original packaging when not in use to protect it from dust and contamination. • Do not expose to direct sunlight or heat sources. • The product should be stored vertically to ensure its quality is not compromised.

### Printing Methods

• Specially developed for Solvent, Latex, UV and UV gel printing. • To ensure the best possible print quality, please check that the correct printing profiles are being used. • Excessive ink application on the product may cause changes in its characteristics, improper drying, delamination, and/or poor product performance. Inadequate drying may result in curling, wrinkling, and adhesion failures, affecting the material's performance. • A minimum drying time of 48 hours is recommended before any additional processing. Drying should be carried out with the product unrolled. • It is recommended that this product be protected with the recommended lamination to provide the necessary resistance.

### Applications

• Application surface: flat and slightly curved. • Applications: Indoor and outdoor advertising of short and medium duration. • Substrate not recommended for areas with car traffic; flexible or low energy substrates; non-flat surfaces; painted or unpainted cardboard walls; plaster walls; wallpaper; unclean or rough surfaces; surfaces with degraded paint. • Do not expose to combustible vapors or spills. • Surfaces to which the material will be applied must be thoroughly cleaned and free of dust or any other contamination that could affect the material's adhesion. • Non-vertical application implies a significant reduction in durability, as do climate and sun exposure angles. • Before using the film, we recommend that it remains at the workplace temperature for at least 24 hours. • Application to damp surfaces or wet application may result in adhesive residue being left on the surface after removal. As no two surfaces are the same, it is recommended that tests are carried out before use to check the removability. • There may be other factors not described which could influence performance in use.

### Important Remarks

• BIOND is not responsible for the ease or speed of removal of the applied material. Suitable air and substrate temperatures must be taken into account. • The user must determine the compatibility of the material with the specific application before use. • The data contained in this information is based on our knowledge and practical experience. It is intended as a source of information and does not constitute a guarantee. Subject to change without notice. • When carrying out a job, we recommend using the same batch of product. • The user must determine the compatibility of the material with the specific application intended before use. • BIOND accepts no liability for misuse or improper storage and can never be held responsible for loss or damage to third parties.